



United States
513.731.1110

France
+33(0) 3.29.37.88.22

Japan
81.3.3344.3010

China
86.21.6064.9669

BiCAT ® 8106

Technical Specifications

Bismuth	19.5 - 20.5%
Nonvolatiles (3 hrs @ 105°C)	85% min
Water	1.0 %
Hexane Insolubles	1.00%
Color (Gardner)	7 max.
Specific Gravity @ 25°C	1.10 - 1.25
Viscosity (Brookfield) @25°C	250 Pse

Product Number

2774C

Description:

Amber liquid with a fatty acid odor.

Application:

Polyurethanes

Packaging:

200 kg- 55 gallon steel closed head drums

Chemical Formula:

Manufactured under ISO 9001 registered quality management systems.

Description

Bismuth carboxylates accelerate the reaction between isocyanates and polyols (the urethane reaction) without promotion of any detrimental side-reactions (e.g. water-isocyanate reaction, hydrolysis of esters). As expected, the rate of the urethane catalysis is directly proportional to the concentration of bismuth in the system. We offer a range of bismuth carboxylate catalysts, with varying bismuth concentrations (from 16 wt% – 28 wt%) and varying ligands (2-ethylhexanoic acid, neodecanoic acid). Our bismuth carboxylate catalysts are environmentally benign options to industry standard lead, tin, mercury and tertiary amine catalysts. BiCAT® 8210 is our highest concentration bismuth carboxylate at 28 wt% bismuth. This material has been successfully used in one- and two-component systems for ambient or heat cure systems. Additionally, BiCAT® 8210 has been successfully used in HFO-based polyurethane spray foam systems.

BiCAT® 8106 is our low free acid bismuth carboxylate at 20 wt% bismuth. This material has been successfully used in one- and two-component systems for ambient or heat cure systems. Additionally, BiCAT® 8106 has been successfully used in HFO-based polyurethane spray foam systems.

Bismuth carboxylates are also interesting from a structural vantage point. With long-chain carboxylic acids they are often viscous liquids even at high bismuth concentration (e.g. bismuth 2-ethylhexanoate at 28 wt% bismuth is a liquid with a viscosity of ≤ 30 Poise at 25 °C). In 2009, we reported the molecular structure of our viscous bismuth carboxylates as part of a presentation on general metal carboxylate structure at the Spring 2009 Annual Meeting of the American Chemical Society. The structures of bismuth

neodecanoate contain clusters, likely $\text{Bi}_2(\text{OOC10H19})_6$ and/or $\text{Bi}_4(\text{OOC10H19})_{12}$, that can reversibly polymerize when the free carboxylic acid concentration is reduced to a minimum (or, as the bismuth concentration is maximized). Bismuth 2-ethylhexanoate (Bi Oct, bismuth octoate) behaves similarly. Interestingly, the bismuth carboxylates show long-range structure (based on X-ray scattering data) that is reminiscent of liquid crystals.

4900 Beech Street, Norwood OH 45212 • P:513-731-1110 • www.shepchem.com

The management system governing the manufacture of this product is ISO 9001:2015 and RCMS®:2013 certified.